

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

This listing of claims will replace all prior versions, and listings, of claims in the application:

LISTING OF CLAIMS

1. (Previously Presented) A a process for the catalytic gas-phase oxidation of propene to acrylic acid, comprising:

passing in which a reaction gas starting mixture 1 which ~~contains propene~~, comprises molecular oxygen and propene in a molar $O_2:C_3H_6$ ratio of ≥ 1 , and at least one inert gas; ~~comprising which comprises~~ at least 20% by volume of molecular nitrogen, ~~and which contains the molecular oxygen and the propene in a molar $O_2:C_3H_6$ ratio of ≥ 1~~ is first passed, in a first reaction stage at elevated temperatures, over a first fixed-bed catalyst, whose active material is at least one multimetal oxide ~~containing~~ comprising molybdenum and/or tungsten and bismuth, tellurium, antimony, tin and/or copper,

thereby obtaining a product gas mixture 1;

wherein said passing of said reaction gas starting mixture 1 proceeds in such a way that the

a propene conversion in a single pass is ≥ 90 mol%, ~~and the~~

an associated selectivity of ~~the~~ an acrolein formation and of ~~the~~ an acrylic acid byproduct formation together is ≥ 90 mol%,

optionally, the a temperature of ~~the~~ said product gas mixture 1 leaving ~~the~~ said first reaction stage is, ~~if required~~, reduced by indirect and/or direct cooling, and, ~~if required~~

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

optionally, molecular oxygen and/or inert gas are/is added to ~~the~~ said product gas mixture 1, and

passing said ~~the~~ product gas mixture 1, as reaction gas starting mixture 2 which ~~comprises contains acrolein~~, molecular oxygen and acrolein in a molar $O_2:C_3H_4O$ ratio of ≥ 0.5 , and at least one inert gas, ~~comprising which comprises~~ comprising at least 20% by volume of molecular nitrogen, ~~and which contains the molecular oxygen and the acrolein in a molar $O_2:C_3H_4O$ ratio of ≥ 0.5~~ , is then passed, in a second reaction stage at elevated temperatures, over a second fixed-bed catalyst whose active material is at least one molybdenum- and vanadium-containing multimetal oxide,

thereby obtaining a product gas mixture 2.

wherein said passing of said reaction gas starting mixture 2 proceeds in such away that

an ~~the~~ acrolein conversion in a single pass is ≥ 90 mol%, and the selectivity of the acrylic acid formation balanced over both reaction stages is ≥ 80 mol%, based on propene converted;;

wherein

- a) ~~the~~ a loading of ~~the~~ said first fixed-bed catalyst with the propene contained in reaction gas starting mixture 1 is ≥ 160 l(S.T.P.) of propene/l of catalyst bed h,
- b) ~~the~~ said first fixed-bed catalyst ~~consists of~~ comprises a catalyst bed arranged in two spatially successive ~~reactor~~ reaction zones A, B, ~~the~~

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

wherein a temperature of reaction zone A ~~being is~~ from 300 to 390°C and ~~the a~~ temperature of reaction zone B ~~being is~~ from 305 to 420°C and at the same time at least 5°C above the temperature of reaction zone A,

- c) the reaction gas starting mixture 1 flows first through reaction zone A and then through reaction zone B,
- d) the reaction zone A extends to a propene conversion of from 40 to 80 mol%,
- e) ~~the a~~ loading of ~~the said~~ second fixed-bed catalyst with the acrolein contained in reaction gas starting mixture 2 is ≥ 140 l(S.T.P.) of acrolein/l of catalyst bed \cdot h,
- f) ~~the said~~ second fixed-bed catalyst ~~consists of~~ comprises a catalyst bed arranged in two spatially successive reaction zones C,D,
the

wherein a temperature of reaction zone C ~~being is~~ from 230 to 270°C and ~~the a~~ temperature of reaction zone D ~~being is~~ from 250 to 300°C and at the same time at least 5°C above the temperature of reaction zone C,

- g) the reaction gas starting mixture 2 flows first through reaction zone C and then through reaction zone D, and
- h) the reaction zone C extends to an acrolein conversion of from 55 to 85 mol%.

2. (Original) A process as claimed in claim 1, wherein the reaction zone A extends to a propene conversion of from 50 to 70 mol%.

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

3. (Original) A process as claimed in claim 1, wherein the reaction zone A extends to a propene conversion of from 65 to 75 mol%.

4. (Previously Presented) A process as claimed in claim 1, wherein the reaction zone C extends to an acrolein conversion of from 65 to 80 mol%.

5. (Previously Presented) A process as claimed in claim 1, wherein the temperature of the reaction zone B is at least 10°C above the temperature of the reaction zone A.

6. (Previously Presented) A process as claimed in claim 1, wherein the temperature of the reaction zone D is at least 20°C above the temperature of the reaction zone C.

7. (Previously Presented) A process as claimed in claim 1, wherein the temperature of the reaction zone B is from 305 to 340°C.

8. (Previously Presented) A process as claimed in claim 1, wherein the temperature of the reaction zone B is from 310 to 330°C.

9. (Previously Presented) A process as claimed in claim 1, wherein the temperature of the reaction zone C is from 245 to 260°C.

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

10. (Previously Presented) A process as claimed in claim 1, wherein the temperature of the reaction zone D is from 265 to 285°C.

11. (Previously Presented) A process as claimed in claim 1, wherein the propene conversion in a single pass in the first reaction stage is ≥ 94 mol%.

12. (Previously Presented) A process as claimed in claim 1, wherein the selectivity of the acrolein formation and of the acrylic acid byproduct formation together in a single pass in the first reaction stage is ≥ 94 mol%.

13. (Previously Presented) A process as claimed in claim 1, wherein the acrolein conversion in a single pass in the second reaction stage is ≥ 94 mol%.

14. (Previously Presented) A process as claimed in claim 1, wherein the selectivity of the acrylic acid formation balanced over both reaction stages is ≥ 85 mol%, based on propene converted.

15. (Previously Presented) A process as claimed in claim 1, wherein the propene loading of the first fixed-bed catalyst is ≥ 165 l(S.T.P.)/l · h.

16. (Previously Presented) A process as claimed in claim 1, wherein the propene

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

loading of the first fixed-bed catalyst is $\geq 170 \text{ l(S.T.P.)}/\text{l} \cdot \text{h}$.

17. (Previously Presented) A process as claimed in claim 1, wherein the at least one inert gas contained in the reaction gas starting mixture 1 comprises $\geq 40\%$ by volume of molecular nitrogen.

18. (Previously Presented) A process as claimed in claim 1, wherein the at least one inert gas contained in the reaction gas starting mixture 1 comprises $\geq 60\%$ by volume of molecular nitrogen.


19. (Previously Presented) A process as claimed in claim 1, wherein the at least one inert gas contained in the reaction gas starting mixture 1 comprises steam.

20. (Previously Presented) A process as claimed in claim 1, wherein the at least one inert gas contained in the reaction gas starting mixture 1 comprises CO_2 and/or CO .

21. (Previously Presented) A process as claimed in claim 1, wherein the propene content of the reaction gas starting mixture 1 is from 4 to 15% by volume.

22. (Previously Presented) A process as claimed in claim 1, wherein the active material of the first fixed-bed catalyst is at least one multimetal oxide of the formula I

Application No.: 09/936,184
 Amendment Dated: August 7, 2003
 Reply to Office Action of: May 7, 2003



where

X^1 is nickel and/or cobalt,

X^2 is thallium, an alkali metal and/or an alkaline earth metal,

X^3 is zinc, phosphorus, arsenic, boron, antimony, tin, cerium, lead and/or tungsten,

X^4 is silicon, aluminum, titanium and/or zirconium,

a is from 0.5 to 5,

b is from 0.01 to 5,

c is from 0 to 10,


d is from 0 to 2,

e is from 0 to 8,

f is from 0 to 10 and

n is a number which is determined by the valency and frequency of the elements other than oxygen in I.

23. (Currently Amended) A process as claimed in claim 1, wherein the active material of the first fixed-bed catalyst is at least one multimetal oxide of the formula II



where

Y^1 is bismuth, tellurium, antimony, tin and/or copper,

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

Y^2 is molybdenum and/or tungsten,

Y^3 is an alkali metal, thallium and/or samarium,

Y^4 is an alkaline earth metal, nickel, cobalt, copper, manganese, zinc, tin, cadmium and/or mercury,

Y^5 is iron, chromium, cerium and/or vanadium,

Y^6 is phosphorus, arsenic, boron and/or antimony,

Y^7 is a rare earth metal, titanium, zirconium, niobium, tantalum, rhenium, ruthenium, rhodium, silver, gold, aluminum, gallium, indium, silicon, germanium, lead, thorium and/or uranium,

a' is from 0.01 to 8,

b' is from 0.1 to 30,

c' is from 0 to 4,

d' is from 0 to 20,

e' is from 0 to 20,

f is from 0 to 6,

g' is from 0 to 15,

h' is from 8 to 16,

x', y' are numbers which are determined by the valency and frequency of the elements other than oxygen in II and

p, q are numbers whose ratio p/q is from 0.1 to 10,

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

b₁
containing three-dimensional regions which are delimited from their local environment as a result of their composition differing from their local environment and have the chemical composition Y_a^1, Y_b^2, O_x , and whose maximum diameters are from 1 nm to 100 μm .

24. (Previously Presented) A process as claimed in claim 1, wherein the first fixed-bed catalyst comprises annular and/or spherical catalysts.

25. (Original) A process as claimed in claim 24, wherein the ring geometry is the following:


external diameter: from 2 to 10 mm,
length: from 2 to 10 mm,
wall thickness: from 1 to 3 mm.

b₂
26. (Currently Amended) A process as claimed in claim 24, wherein the spherical catalyst is a coated catalyst ~~consisting of~~ comprising a spherical support having a diameter of (from 1 to 8 mm ~~diameter~~) and a coat of active material applied thereon having a thickness of (from 10 to 1000 μm ~~thick~~).

27. (Previously Presented) The process as claimed in claim 1, wherein the first and the second reaction stages are each carried out in a two-zone tube-bundle reactor.

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

28. (Previously Presented) A process as claimed in claim 1, wherein the active material of the second fixed-bed catalyst is at least one multimetal oxide of the formula IV



where

X¹ is W, Nb, Ta, Cr and/or Ce,

X² is Cu, Ni, Co, Fe, Mn and/or Zn,

X³ is Sb and/or Bi,

X⁴ is one or more alkali metals,

X⁵ is one or more alkaline earth metals,

X⁶ is Si, Al, Ti and/or Zr,

a is from 1 to 6,

b is from 0.2 to 4,

c is from 0.5 to 18,

d is from 0 to 40,

e is from 0 to 2,

f is from 0 to 4,


g is from 0 to 40 and

n is a number which is determined by the valency and frequency of the elements other than oxygen in IV.

29. (Previously Presented) A process as claimed in claim 1, wherein the active

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003

material of the second fixed-bed catalyst is at least one multimetal oxide of the formula VI



where

D is $Mo_{12}V_{a''}Z^1_{b''}Z^2_{c''}Z^3_{d''}Z^4_{e''}Z^5_{f''}Z^6_{g''}O_{x''}$,

E is $Z^7_{12}Cu_hH_{i''}O_{y''}$,

Z^1 is W, Nb, Ta, Cr and/or Ce,

Z^2 is Cu, Ni, Co, Fe, Mn and/or Zn,

Z^3 is Sb and/or Bi,

Z^4 is Li, Na, K, Rb, Cs and/or H,

Z^5 is Mg, Co, Sr and/or Ba,

Z^6 is Si, Al, Ti and/or Zr,

Z^7 is Mo, W, V, Nb and/or Ta,

a'' is from 1 to 8,

b'' is from 0.2 to 5,

c'' is from 0 to 23,

d'' is from 0 to 50,

e'' is from 0 to 2,

f'' is from 0 to 5,

g'' is from 0 to 50,

h'' is from 4 to 30,

i'' is from 0 to 20 and

Application No.: 09/936,184
Amendment Dated: August 7, 2003
Reply to Office Action of: May 7, 2003


x",y" are numbers which are determined by the valency and frequency of the elements other than oxygen in VI and

p,q are numbers other than zero whose ratio p/q is from 160:1 to 1:1,

which is obtainable by separately preforming a multimetal oxide material (E)



in finely divided form (starting material 1) and then incorporating the preformed solid starting material 1 into an aqueous solution, an aqueous suspension or a finely divided dry blend of sources of the elements Mo, V, Z¹, Z², Z³, Z⁴, Z⁵, Z⁶, which contains the abovementioned elements in the stoichiometry D



(starting material 2), in the desired ratio p:q, drying any resulting aqueous mixture, and calcining the dry precursor material thus obtained, before or after it has been dried, at from 250 to 600°C to give the desired catalyst geometry.

30. (Previously Presented) A process as claimed in claim 1, wherein the second fixed-bed catalyst comprises annular catalysts.

31. (Previously Presented) A process as claimed in claim 1, wherein the second fixed-bed catalyst comprises spherical catalysts.